

DEK STANDARD ENGINEERING INSTRUCTION

Title

Page 1 of 1

Bundy Tube

DSM171

Constructed from copper coated steel strip rolled twice around laterally, furnace brazed to produce a tube of double wall structure of consistently uniform wall thickness.

Sizes Available

O/D		I/D		Min Bending Radius	
Inch	mm	Inch	mm	Inch	mm
3/16	4	0.131	2.6	3/8	10
1/4	6	0.194	4.6	1/2	13
5/16	8	0.256	6.6	3/4	19
3/8	10	0.319	8.6	7/8	22
1/2	12	0.444	10.6	1 3/4	44

Issue	01	02	03	04	05	06	07	08
DCR	7135							