

THERMOPLASTIC

SEMI-CRYSTALLINE GROUP

Definition:

It is the long chained molecules that define the character of this group. When moulded, this highly ordered molecular structure is anisotropic: shrinking less in the direction of flow vs. transverse to flow. Other features of this aligned structure include a high degree of component flexibility, good chemical & ESC (Environmental Stress Cracking) resistance.

Semi-crystalline materials have a distinctive (known) melting temperature, they do not gradually soften when exposed to increases in temperature, instead they remain solid until a given quantity of heat is absorbed then rapidly change into a low viscous (watery) melt.

Typical Features:

- Chemical & ESC resistant.
- Fatigue resistant & flexible
- Good for bearing & wear.
- Resistant to bonding with solvents & adhesives.
- Distinctive (known) melting temperature.

Reinforcements & fillers:

Benefits, if available:-

Glass fibre **reinforcement** by weight (eg: 30%) alters Mechanical

Properties:-

- Increases stiffness
- Becomes more brittle.
- Reduces moulding shrinkage.
- Improvements to Heat Distortion Temp (HDT).

Additional **fillers** can improve:-

- Flame-retardance.
- Electrical properties:-

Carbon increases conductivity

Stainless steel improves dissipative behaviour.

Issue	01	02	03	04	05	06	07	08	09
DCR	44896								



DSM 4.3.1

POLYPROPYLENE_DISSIPATIVE (Cadmium Yellow)

General:

Polypropylene (PP) is the most versatile & cost effective of the polyolefin (wax-like feel) family.

Benefits:

- Resistant to fatigue, flexible with moderate strength.
- It has good impact strength, surface hardness, dimensional stability and excellent abrasion resistance.
- Polypropylene does not present stress cracking problems & is resistant to a wide variety of acids, alkalis and solvents.
- Non hygroscopic.
- PP doesn't melt below 160°C.

PP homopolymer: For general use. Stronger & stiffer than copolymer.

PP copolymer: Tougher & more durable, where higher impact qualities are required.

Limitations: (unmodified)

- Degraded by UV.
- Flammable.
- Attacked by chlorinated solvents (carbon tetrachloride) & aromatics (Benzene)
- Difficult to bond & paint.

ASM (DEK) Applications:

- Hose Clip & Under screen cleaner components

These values are representative. For critical applications, refer to data-sheet.

MECHANICAL PROPERTIES					
	HARDNESS Shore A	TENSILE STRENGTH:	YOUNGS MODULUS:	POISSONS RATIO:	DENSITY:
>PP<	---	28 MPa	1.55 GPa	0.36	930 Kg/m ³

HOMOPOLYMER GRADE	SUPPLIER	UL No.	RECYCLE CODE
ECP 2200 + Master Batch Colour RAL 1021	TBA Protective Solutions	----	>PP <

Alternatives: Alternative polymers are allowed only with the express written permission of ASMPT. Please email details of your request to engineering_enquiries@asmpt.com

Issue	01	02	03	04	05	06	07	08	09
DCR	44896								