

DEK STANDARD ENGINEERING INSTRUCTION

Title

Page 1 of 1

Aluminium Extruded Bar

DSM218

Preferred

6082 (H30) to BS 1474: 1987

Applications

A medium strength alloy used in structured applications. Good strength and corrosion resistance. Decorative anodising response is FAIR. Cold formability is GOOD.

Tensile Strength: 170-200 N/mm²(TB) 295-310 N/mm² (TF)

Available Forms

Angle

Square

Round and Tube

Flat

Channel

Issue	01	02	03	04	05	06	07	08
DCR	7135							