

DEK STANDARD ENGINEERING INSTRUCTION

Title

Page 1 of 2

PAINT: Heat Resistant to 600°C

DSF200

PAINT TYPE

Temalac SA100

MANUFACTURER:

Macphersons Paints Ltd.,
Radcliffe Road,
Bury,
BL9 NB.

DESCRIPTION

A single pack, high temperature, high build Silicone Aluminium.

FEATURES

Resists temperatures up to 650°C,
Can be applied as a single coat without need of a sealer coat.
British Gas PA9 Approved.
Can be applied to Blast Cleaned Steel.

FILM THICKNESS

Wet 55/133 Microns
Dry 25/60 Microns

FILM COVERAGE

18.0m²/litre @ 25 Microns Dry.

APPLICATION

Conventional Spray/ Airless Spray/ Brush.

DRYING TIMES

	10°C	23°C	35°C
Dust Free	1 Hour	30 Mins	20 Mins
Hard	3 Hours	1 Hour	40 Mins

COLOUR:

FINISH

Semi-Gloss

Issue	01	02	03	04	05	06	07	08
DCR	7135							

DEK STANDARD ENGINEERING INSTRUCTION

PAINT: Heat Resistant to 600°C

DSF200

PRODUCT NOTES

- 1) Thinners = 1006/Equipment Cleaner 1018
- 2) Do not apply directly to hot surfaces.
- 3) Product needs to reach 200°C for heat curing & maximum performance.
- 4) Flash Point 21-32°C.

SURFACE PREPARATION

Clean & Dry.

HEALTH & SAFETY

Observe normal precautions.

Issue	01	02	03	04	05	06	07	08
DCR	7135							